

پتروشیمی محب بسیار ایده گستر .PMBIG.Co

Parameter	UNIT	TEST Conditions	VALUE
GPPS Grade Number 1109			
Density/Bulk Density	gr/cm ³	ASTM D-1895	1/02
Flexural Modulus	MPA	ASTM 790	2900
Tensile Strength	MPA	ASTM D-638	15
Vicat Softening	°C	ASTM D-1525	98
Heat Distortion-Temperature(HDT)	°C	ASTM D-648	97
Mfi	g/10 min	ASTM D-1238	8
Derermlnation of Residual-Styrene Monomer	ppm	CLGLABPSG004	<500